

Material Safety Data Sheet

Ingersoll Rand Moisture Magnet Chemical Desiccant

Product Description: Moisture absorbing material.

Ingersoll Rand part number: 35387273

CHEMTREC: (800) 424-9300 or (202) 483-7616

SECTION 1 COMPOSITION/ INFORMATION ON INGREDIENTS

COMPONENTS	CAS NUMBER	AMOUNT
Alkali chloride salt		75%

SECTION 2 FIRST AID MEASURES

Eye: Flush with water for 15 minutes.

Skin: Wash with soap and water. Treat for dry skin.

Ingestion:

Inhalation: Remove to fresh air.

SECTION 3 FIRE AND EXPLOSION HAZARD DATA

Flash Point (method used):	Flammable Limits	LEL	UEL
Non-flammable	N/A	N/A	N/A

FIRE FIGHTING PROCEDURES: Standard procedures

EXTINGUISHING MEDIA: Water, foam, CO2, Dry Chemicals

UNUSUAL FIRE AND EXPLOSION HAZARDS: Under extreme fire conditions possibility of metal oxide fumes produced.

SECTION 4 HAZARDOUS INGREDIENTS/ IDENTITY INFORMATION

Hazardous Components	Other Limits:
(Specific Chemical Identity/Common Name(s))	OSHA ACGIH TLV Recommended %optional
1) The ingredients and percentage of ingredients in Moisture Magnet is a trade secret 2) Moisture Magnet does not contain hazardous ingredients 3) Moisture Magnet does not contain any substances found on the following EPA regulations: a. "Extremely Hazardous Substances" b. "CERCLA Hazardous Substances" c. "Toxic Substances"	

SECTION 5 EXPOSURE CONTROLS/PERSONAL PROTECTION

GENERAL CONSIDERATIONS:

Potential Health Effects: Inhalation, skin and eye contact.

Health Hazards (acute and chronic): None known.

Carcinogen city: NTP IARC Monographs? OSHA Regulated?

No No No No

Signs and symptoms of exposure: Skin dryness due to desiccant action.

Medical conditions generally aggravated by exposure: None known

Doosan purchased Bobcat Company from Ingersoll-Rand Company in 2007. Any reference to Ingersoll-Rand Company or use of trademarks, service marks, logos, or other proprietary identifying marks belonging to Ingersoll-Rand Company in this manual is historical or nominative in nature, and is not meant to suggest a current affiliation between Ingersoll-Rand Company and Doosan Company or the products of either.

SECTION 6 PHYSICAL AND CHEMICAL PROPERTIES

Boiling Point:	>1000°C	Specific Gravity (Water=1)	1.6 gms/cc
Vapor Pressure (mm Hg)	> N/A	Melting Point	235°F
Vapor Density (Air=1)	> N/A	Evaporation Rate	
Solubility in Water	> 100%	(Butyl Acetate=1)	N/A
Appearance and Odor:	Tablet – ¾" x 5/8"; used in a sealed pressure vessel as a desiccant. White tablets with pick specs, odorless.		

SECTION 7 STABILITY AND REACTIVITY

Stability (conditions to avoid):	Stable. Exposure to atmosphere; tablets will attract water.
Incompatibility (Materials to avoid):	N/A
Hazardous decomposition/byproducts:	None
Hazardous Polymerization:	Will not occur

SECTION 8 PRECAUTIONS FOR SAFE HANDLING AND USE

Small/Large Spills: No special precautions. Material can be cleaned up with shovels, brooms and/or water

Waste and disposal Method: Treat tablets as ordinary non-combustible solid waste. Solution is non-toxic
And will not support plant or marine life.

Handling and Storage: Mixture is non-toxic. Respiratory protection as needed. Store in cool, dry place. Keep
Containers closed since material is hygroscopic and deliquescent.

Other Precautions: Before storing tape and repair torn bags.

SECTION 11 CONTROL MEASURES

Respiratory Protection (specific type): Avoid inhaling dust. Use respirator for dusty conditions.

Ventilation: Use adequate ventilation	Local exhaust Yes	Mechanical N/A
	Special N/A	Other N/A

Protective Gloves: In case of open cuts or sensitive skin

Eye protection: Normal protection against dust and dirt.

Other protective Clothing & Equip: Use safety equipment when required

Work/Hygienic Practices: There is no need to contact tablets with bare hands.

The above information is based on the data of which we are aware and is believed to be correct as of the date hereof. Since this information may be applied under conditions beyond our control and with which we may be unfamiliar and since data made available subsequent to the date hereof may suggest modifications of the information, we do not assume any responsibility for the results of its use. This information is furnished upon condition that the person receiving it shall make his own determination of the suitability of the material for his particular purpose.